



# GDF DC 20/130-0.08

## Double-Clad Passive Optical Fiber

Product Number	DG1111-A
----------------	----------

### Optical Properties

Core NA	$0.08 \pm 0.01$
Inner Cladding NA	$\geq 0.46$
Core Attenuation @1300nm (dB/km)	$\leq 40.0$
Core Attenuation @1200nm (dB/km)	$\leq 20.0$
Cladding Attenuation @1095nm (dB/km)	$\leq 15.0$

### Geometric / Mechanical Properties

Core Diameter ( $\mu\text{m}$ )	$20.0 \pm 1.5$
Cladding Diameter ( $\mu\text{m}$ )	$130.0 \pm 1.0$
Coating Diameter ( $\mu\text{m}$ )	$245.0 \pm 10.0$
Core / Cladding Concentricity ( $\mu\text{m}$ )	$\leq 0.7$
Cladding Non-circularity (%)	$\leq 0.5$
Proof Test (kpsi)	$\geq 100$

\*Single-clad optical fiber products can be provided according to customer needs