

GDF DC 20/400-0.065

Polarization Maintaining Passive Double-Clad Optical Fiber



Product Number

DG1118-G

Optical Properties

Core NA	0.065 ± 0.005
Inner Cladding NA	≥ 0.46
Birefringence	4×10^{-4} (typical)
Cladding Attenuation @1095nm (dB/km)	≤ 15.0

Geometric / Mechanical Properties

Core Diameter (μm)	20.0 ± 1.5
Cladding Diameter (μm)	400.0 ± 5.0
Coating Diameter (μm)	550.0 ± 15.0
Proof Test (kpsi)	≥ 100